SEPIOLSA
Minersa Group

0019020

SPECIFICATION SHEET

SEPIOLITE 4-30
Industrial Absorbent

Composition (XRD)	
Sepiolite	65% (Min. 60%)

Physical properties	
Density	0.70 g/cc (Max. 0.77 g/cc)
Westinghouse water absorption	85% (Min. 75%)
Westinghouse oil absorption	35% (Min. 30%)

Particle size distribution	
> 4.75 mm	Max. 3.5%
4.75 mm - 0.50 mm	Min. 94.5%
< 0.50 mm	Max. 2%